

CREA 8012 Slip

BRICK SLIPS
CATEGORY I, U



TEXTURE, TYPE & COLOUR

All our slips are available with a thickness of approximately 20 mm as standard. In addition to the classic brick slip, you can also obtain corner slips and horizontal corner slips with this thickness. At your request, we can also look at the possibilities of producing other infill pieces and thicknesses. The slips have the same technical characteristics as the basic bricks from which they are made. The technical characteristics of the basic brick are shown below. The bricks are through-coloured and the colour is red purple.

TECHNICAL CHARACTERISTICS

The bricks are delivered with the following characteristics, in accordance with the CE and UKCA mark:

CE mark according to EN 771-1: 2011 + A1: 2015 and UKCA mark according to BS EN 771-1 : 2011 + A1 : 2015

Manufacturing dimensions (L x W x H)	: *212x20x63 mm
Quantity / m ² with a traditional joint	: ca. 59
Size tolerance	: T1
Gross mass density	: 1900 kg/m ³ (+/- 20 %)
Water absorption (24 hours)	: < 12%
Initial water absorption (1 minute)	: < 4 kg/(m ² . min) IW3
Water vapour permeability	: $\mu = 5/10$
Thermal properties (λ_{10} , dry, 90/90)	: 0.60 W/mK (table 1 EN1745)
Durability (frost / thaw / resistance)	: F2 – highly frost-resistant
Active soluble salts	: class S2
Fire reaction	: class A1
Bond strength (according to EN998-2: 2003 Annex C)	: NPD (no performance determined)



VANDE MOORTEEL
CLAY PAVERS • FACING BRICKS • SLIPS

ORIGIN : VANDE MOORTEEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel.co.uk

CREA 8012 Slip

Productshot



VANDE MOORTELE
CLAY PAVERS • FACING BRICKS • SLIPS

ORIGIN : VANDE MOORTELE NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel.co.uk