



TEXTURE, TYPE & COLOUR

All our slips are available with a thickness of approximately 20 mm as standard. In addition to the classic brick slip, you can also obtain corner slips and horizontal corner slips with this thickness. At your request, we can also look at the possibilities of producing other infill pieces and thicknesses. The slips have the same technical characteristics as the basic bricks from which they are made. The technical characteristics of the basic brick are shown below. The colour of the body is brown-red and ranges from aubergine-red to red-brown with an irregular beige-white surface texture with a lot of nuances and a few light yellowish accents.

TECHNICAL CHARACTERISTICS

The bricks are delivered with the following characteristics, in accordance with the CE and UKCA mark:

CE mark according to EN 771-1: 2011 + A1: 2015 and UKCA mark according to BS EN 771-1 : 2011 + A1 : 2015

Manufacturing dimensions (L x W x H)	: *220x20x52 mm	
Quantity / m ² with a traditional joint	: ca. 68	
Number / m ² with a thin joint	: ca. 77	
Manufacturing dimensions (L x W x H)	: *215x20x65 mm	- On demand > 2000 m ²
Size tolerance	: Tm (+/- 8/6/4)	
Gross mass density	: 1900 kg/m ³ (+/- 20 %)	
Water absorption (24 hours)	: < 16%	
Initial water absorption (1 minute)	: < 4 kg/(m ² . min) IW3	
Water vapour permeability	: μ = 5/10	
Thermal properties (λ10, dry, 90/90)	: 0.60 W/mK (table 1 EN1745)	
Durability (frost / thaw / resistance)	: F2 – highly frost-resistant	
Active soluble salts	: class S2	
Fire reaction	: class A1	
Bond strength (according to EN998-2: 2003 Annex C)	: NPd (no performance determined)	

Brick B Slip

Productshot



VANDE MOORTEEL
CLAY PAVERS • FACING BRICKS • SLIPS

ORIGIN : VANDE MOORTEEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel.co.uk