

SeptimA Colosseum



COLOUR

Anthracite.

Product description

The bricks are formed individually in the sanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an sanded surface structure. The shape is slightly irregular. Finally the bricks are processed until they have acquired a weathered shape, due to which the paver surface leaves a rustic, aged impression.

TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the Benor mark, the CE mark and UKCA mark.

CE label according to EN 1344 : 2013 / AC : 2015

Manufacturing dimensions (L x W x H) : *217x52x70 mm

Quantity / m² with a traditional joint : ca. 85

PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

Aspect	Class	Mean	Individual
Water absorption NBN EN771	W3	Max 3%	Max 4%
Transverse breaking load	T4	Min 80 N/mm	Min 64 N/mm
Abrasion resistance	A3	Max 450 mm ³	Max 500 mm ³
Frost resistance	FP100	freeze/thaw resistant	freeze/thaw resistant
Wet skid resistance	U3	>55	
Acid resistance	C	< 7%	
Size tolerance*	NPD	NPD	NPD

SeptimA Colosseum

Productshot



VANDE MOORTELE
CLAY PAVERS • FACING BRICKS • SLIPS

ORIGIN : VANDE MOORTELE NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel.co.uk